



CLIENT: Knight Industries, LLC

Report No.: 176906

Date: 06/02/03

Page: 5 of 9

RESULTS:

Resistance to Chemicals

<u>Specimen #</u>	<u>Chemical</u>	<u>Surface Dulling</u> 0 - 3	<u>Surface Attack</u> 0 - 3	<u>Color Change</u> 0 - 3
1	White Vinegar	0	0	0
2	Rubbing Alcohol	1	0	0
3	White Mineral Oil	0	0	0
4	Sodium Hydrol Solution	1	0	0
5	Hydrochloric Acid Solution	0	0	0
6	Sulfuric Acid 5% Solution	0	0	0
7	Ammonia	2	0	0
8	Household Bleach	0	0	0
9	Olive Oil	0	0	0
10	Kerosene	0	0	0
11	Unleaded Gasoline	0	0	0
12	Phenol	1	0	1
13	Coca	0	0	0
14	Ketchup	0	0	0
15	Mustard	0	0	1
16	Anti-Freeze	0	0	0
17	Gasoline	0	0	0
18	Transmission Fluid	0	0	0
19	Sulfuric Acid 10% Solution	0	0	0
20	Iodine 2%	0	0	3
21	Betadine 10%	0	0	0

0 = No Change

1 = Slight Change

2 = Moderate Change

3 = Severe Change

Requirements: No more than a slight change in surface dulling, surface attack, or staining.